

RAW MATTS TESTS

Δ 9/10 clay bodyS :

white porcelain

grolleg	45	→	EPK	30
xx sagger	10		grolleg	10
cluster	20		tile 6	10
pyrax	12		xx sag	15
Flint	13		cluster	20
			Flint	13
			Pyrex	12

Pearly body Δ 9/10

gold art	20		EPK	10
xx sagger	15		tile 6	10
EPK	15		xx sagger	15
Prandy blk	10		cluster	20
Fine clay	20		Flint	13
FLint	5		Pyrex	12
cluster	10			

(1/2% lutid optical)

Flameware body

A.P. green missouri	20
gold art	20
tenu ball	2
petalite	57
g. brate	1
mucaloid	2%