

Richard Haynes
MFA 1988

RELATED TECHNICAL DATA

Clay

Porcelain Throwing Body	cone 10	
Georgia Tile #6 Kaolin		35
English China Clay (Grolleg)		10
Edgars Plastic Kaolin		10
Ball Clay (lowest Iron content available)		10
Oxford Feldspar (Posash)		15
Flint		15
Pyrax		5
		<hr/>
		100

+ Macaloid 1/2%

White Slip cone 10

Same formula as clay body with the following exceptions:

Ball Clay was omitted but is optional
Macaloid was omitted but is optional

Glazes

Satin White Matt	cone 9 - 10	reduction	
Neph. Syn.			45
Talc			7
Dolomite			10
Whiting			8
Flint			30
			<hr/>
			100

+ Bentonite 3%

Note: the addition of 10% Black Stain to this glaze produces a flat satin black