

# RANDY JOHNSTON GLAZE RECIPES AND CLAY BODIES

## TRAILING WHITE GLAZE A9

7 lbs. 8 oz. Custer spar  
 1 lb. Talc  
 1 lb. EPK  
 8 oz. Tin oxide

+ 8 oz ZIRLOPAX

## TRAILING BLACK GLAZE A9

7 lbs. 8 oz. Custer spar  
 1 lb. Talc  
 1 lb. EPK  
 8 oz. Mason black #6609

## ABT A10 Stony thin base for Mashiko Kaki

50 parts Custer spar  
 25 parts Whiting  
 30 parts EPK  
 5 parts Flint

## NUKA A9-10

37.5 lbs. Custer spar  
 2.5 lbs. EPK  
 4 lbs. Ash  
 2 lbs. Flint  
 5 lbs. Nepheline syenite  
 .5 lbs. Tin oxide

## JOHNSTON PORCELAIN GLAZE

6.4 lbs.	Custer spar	2905.6	5811.2
2.4 lbs.	Whiting	1089.6	2179.2
2.4 lbs.	Talc	1089.6	2179.2
5.7 lbs.	EPK	2587.8	5175.6
4.4 lbs.	Silica	1997.6	3995.2
.64 lbs.	Magnesium carbonate	290.56	581.12

## JOHNSTON WHITE SLIP FOR SALT BISQUE APPLICATION

14.6 lbs. Avery kaolin  
 5.2 lbs. Custer spar  
 4 lbs. Silica  
 250 g. Bentonite

TENMOKU

Custer	54	
Whiting	13	
Barium Carb	2.5	ZINCOX 2.5
EPK	6	Red Iron Ox 7.
Flint		

## JOHNSTON WHITE SLIP FOR DAMP

25% EPK  
 25% Ball clay  
 25% Custer spar  
 25% Silica

## TRAILING BLACK SLIP

2 Tbsp. Mason black #6609  
 24 oz. Liquid slip

## JOHNSTON STONEWARE CLAY BODY

100 lbs. Missouri Fire Clay (APG)  
 12 lbs. Custer spar  
 10-15% Fine grog for handbuilding

## JOHNSTON PORCELAIN CLAY BODY

55 lbs. Grolleg  
 15 lbs. Flint  
 15 lbs. Pyrophyllite  
 22 lbs. Custer spar  
 3 lbs. Bentonite  
 10% Fine Molochite for handbu

BRAY SHINO

KONA F-4	8.1
Spod	6.68
Soda ash	1.76
Neph sy	19.82
OM4	7.2