

110 PINNELL CLEAR (BABU'S BASE GLAZE)

Custer 2500

Silica 3500

Whiting 2000

GRULLER 2000

To 10,000 grms.

ADD 1/4 cup MURIATIC ACID

\*

COLOR VEHICLE FOR PAINTING  
OVER PINNELL CLEAR

50 COLOR

20 BALL CLAY

30 FRIT 3110

1 TBS CMC TO

4 CUPS WATER

D LUSTER SHINO

NEPH Sy 5300

EPK 2500

Silica 1000

Whiting 200

SODA ASH 500

Lith Carb. 500

Tin ox. 200

BENTO 200

ACERO

Custer 53

Talc 5

EPK 25

BRASH 27.3

R10 4.1

GOLD MATT

Dolomite 22.5

Whiting 3.5

Custer 49

Ball 25

Rutile 8%

Bent 2%

\* USE 5% COBALT TO PINNELL CLEAR FOR  
DEEP NAVY BLUE OVER GLAZE

- EXAMPLE PINNELL BLUE OVER PINNELL CLEAR

JOHN GILL

Δ 10

A.R. 93

WEISER STONY WHITE

1 Custer 63  
Dolo 24  
Silica 4  
BALL 9  
Bent. 2

POND SCUM GREEN

8% NICKLE SILICATE

HAYDEN RED

Custer 200  
EPK 100  
Whitening 40  
Dolomite 64  
BONE ASH 32  
Tin Ox. 20  
Bent. 04  
RIO 20

BERTAUD BLUE

NEPH SX 50  
EPK 12.5  
Barium CARB. 31.3  
Flint 6.3  
Copper CARB. 3.

FIESTA BLUE

Custer 36.4  
Flint 21.3  
Whitening 18.2  
EPK 9.1  
Zircopax 9.0  
COBALT CARB .5  
Bent ~~2~~ 2

ORIBE

Custer 49  
Whitening 15  
Kaolin 12  
Flint 25  
Copper CARB 7

EMILY PURPLE

Custer 41  
Colemanite 12  
Dolomite 7  
Talc 15  
TENN BALL 5  
Flint 20  
Bentonite 2  
BLACK COBALT 2  
Tin oxide 2