

GLICK/SYMONS GLAZES - CONT'D

GW #11

F-4 SODA SPAR	430 gm.
WHITING	190
BALL CLAY	100
FLINT	280
BENTONITE	30
	<hr/>
	1030 gm.

Variation #1: Cobalt carb 10%
Red Iron Ox. 10%
Titanium Diox. 4%

Variation #2: Red Iron Ox. 15%

C7-D2

SODA SPAR	240 gm.
WHITING	40
EPK	60
GERSTLEY BORATE	20
FLINT	60
BONE ASH	20
BARIUM CARB.	80
	<hr/>
	448 gm.

Variation #1: 10% Black Iron Oxide

S-2 Shino

Soda Ash	3
Kona F-4 spar	15
Neph. Syenite	50
Spodumene	13
E.P.K.	3
Ball Clay	16
	<hr/>
	100

NOTE:

Mix Bentonite into glazes in the dry mix. Then add water.

RHODES #23

ALBANY SLIP	60
CORNWALL STONE	25
Red Iron Oxide	5
WHITING	10
	<hr/>
	106

MG2

SODA SPAR	250 gm.
GERSTLEY BORATE	36
DOLOMITE	44
TALC	88
KAOLIN	30
FLINT	120
TIN OXIDE	18
	<hr/>
	586 gm.

Add 2% Bentonite