

DAVID LEACH'S GLAZES CONT'D

TENMOKU Δ10

CORNISH STONE	66
WHITING	11.5
CHINA CLAY (EPK)	7.5
FUNT	15
RED IRON OXIDE	7.5

CREAM GRAY MATTE Δ9-10

TALC	1 LB. 402
CORNISH STONE	13 LB.
BALL CLAY (OM-4)	5 LB. 1202.
CHINA CLAY (EPK)	1 LB. 402.
WHITING	1002.
WOOD ASH	3 LB. 202.

COPPER RED Δ9

BORAX FRITT	15
F-4 SPAR	45
WHITING	15
CHINA CLAY (EPK)	05
FUNT	20
TIN OXIDE	05
COPPER CARB.	0.5
BENTONITE	1.0

DAVID LEACH CONT'D

CHUN GLAZE Δ9

POTASH SPAR (CUSTAR)	36
FLINT	26
CORNISH STONE	22
WHITING	13
DOLOMITE	03
BONE ASH	01
RED IRON OXIDE	1.0

IRON SLIP Δ 9-10

RED ART CLAY	75
RED IRON OXIDE	25

IRON PIGMENT - (OVERGLAZE)

RED ART CLAY	25
RED IRON OXIDE	75

RED OVERGLAZE

NEPHELINE SYENITE	50
CALCINED RED ART	50

BLUE PIGMENT

COBALT OXIDE	25
RED IRON OXIDE	25
MANGANESE DIOXIDE	25
DRY PORCELAIN BODY	25

DAVID LEACH'S GLAZES

Δ9 DOLOMITE WHITE

FELDSPAR (COSTAR)	45.4
DOLOMITE	17.6
BONE ASH	2.75
KAOLIN (EPK)	22.2
FLINT	2.75
TALC	9.3

Δ9 LIGHT BLUE-GREEN CELADON

CORNISH STONE	25
KAOLIN (EPK)	25
WHITING	25
FLINT	25
RED IRON OXIDE	0.5

Δ9 BLUE-GREEN CELADON

CORNISH STONE	25
KAOLIN	25
WHITING	25
FLINT	25
RED IRON OXIDE	02.0

KRISTEN'S FROG SKIN GLAZE Δ10

GERSTLEY BORATE	36
TALC	45
DOLOMITE	21
CUSTAR SPAR	123
EPK	15
FLINT	65
RED IRON OXIDE	03
RUTILE	02

KRISTEN'S BLUE Δ10

GERSTLEY BORATE	36
TALC	45
DOLOMITE	21
CUSTAR	123
EPK	15
FLINT	65
COBALT CARB.	02
COPPER CARB.	06