

JEFF OESTRICH Δ9-10 GLAZES

CELADON

BALL CLAY	485
WHITING	970
FLINT	1455
CUSTAR	1940
YELLOW OCHRE	150

WHITE

CUSTAR	33.3
EPK	22.2
FLINT	22.2
DOLomite	22.2

SHINO

NEPT SY.	450
F-4 SPAR	108
SPODUMENE	152
OM-4	150
EPK	100
SODA ASH	40

TENMOKU

CUSTAR	4838
WHITING	1164
BARIUM CARB	224
FLINT	2014
ZINC OXIDE	224
RED IRON OXIDE	805
BENTONITE	193

DAVID SHAWER CLEAR Δ 9-10*

F-4 SPAR	1595
WHITING	840
DOLomite	260
KAOLIN	705
FLINT	1545
ZINC OXIDE	250

* Δ8 - SOFT OPAQUE WHITE

JEFF OESTRICH PORCELAIN CELADON Δ 9-10

CUSTAR	5 lbs. + 436 grams
WHITING	4 lbs. + 130 g.
EPK	4 lbs + 163 g.
FLINT	7 lbs. + 91 g
RED IRON OXIDE	————— 124 grams