

# AMBER CELADON

ALBANY SLIP	1650
WOLLASTONITE	650
E.P.K.	150
GERSTLY BORATE	150
WHITING	350
FLINT	650
CUSTER	1000
OCHRE	900

# ETHEL'S RED

CUSTER	4216
TALC	320
KAOLIN	2000
WHITING	1704
BONE ASH	240
R.I.O.	200
RUTILE	200
BENTONITE	177.60

1988

LAVENDER BLUE MATT	
CUSTER	360
KAOLIN	220
D210	100
CALC	40
WHITING	40
FLINT	160

CUBAN CARB 5.  
TO ABOVE BATCH

Seattle Spring  
RAIN

TALC	11.2
WHITING	20.5
CUSTER	32.2
KAOLIN	16.6
FLT.	19.5
RUTILE	8.3

THE APPLICATION

# GEORGE LOWE

## GOOD GREY CELADON 410.

CUSTER	25.3
KONA F4	11.5
FLINT	28
WHITING	6.4
KAOLIN	5.2
GERSTLEY BORATE	5.8
BARIVM CARB.	6.3
DOLOMITE	5.8
ZINC	1.3
ZIRCOPAX	3.7
IRON OX.	.5
COBALT	.007

## BARIVM MATT BASE

NEPH. SY.	500
BARIVM CARB.	400
BALL CLAY	100
WHITING	110

ADD OXIDES FOR COLOR:

RUTILE 100 - YELLOW

DO TESTS FOR DIFFERENT COLORS.

## JADE CELADON 410

CUSTER	32.65
FLINT	30.60
KAOLIN	5.60
WHITING	6.56
GERSTLEY BORATE	7.35
DOLOMITE	7.35
ZINC	1.60
BARIVM	3.95
ZIRCOPAX	2.33
F4	2.33
IRON CHRO.	1.00
IRON OXIDE	.13
COBALT	.11

GREEN GLAZE  
WOLLASTONITE - 100

F-1  
NEPH. SY. 55  
BALL CLAY. 45

## KILLER

WOLLASTONITE	25
NEPH. SY.	25
KAOLIN	25
WOOD ASH	25

## KILN WASH

FLINT	75
KAOLIN	25

## GUSTIN SHINO

F4 FELDSPAR	18.4
SPODUMENE	15.2
OM 4	15.
SODA ASH	4.0
NEPH. SY.	45.
E.P.K.	2.4

## ★ SHINO SLIP

F4 FELDSPAR	10.8
SPODUMENE	15.2
SODA ASH	4.0
NEPH. SY.	45.
OM 4 BALL	15.
E.P.K.	35.

## SHANER KILN WASH

WOOD. ALUMINA 3  
KAOLIN 1  
A HANDFUL OF  
EPSOM SALTS.

## LEWIS YELLOW

DRY - HOT FIRE

F4 FELDSPAR	32.5
BACO <sub>3</sub>	25.28
DOLOMITE	12.15
BALL	7.22
FLINT	7.22
ZIRCOPAX	15.00
RED IRON OX.	2 1/2 %

## FERGUSON VARIATION

F4 FELDSPAR	35.
BACO <sub>3</sub>	25.28
DOLOMITE	12.15
BALL (KAOLIN)	7.22
FLINT	5.
OPAX	15.
R.I.O.	3.9%

(may vary for clay body)

## LEWIS YELLOW

THIN = BROWN  
MED = BRIGHT YELLOW  
THICK = CREAM