

GLAZES USED IN HAYSTACK'S SODA KILN - M. SIMON
 Summer 1993

TESSHA

BALL CLAY 1626
 SILICA 1626
 POTASH SPAR 1500
 WHITING 1080
 RED IRON OX. 660

GUSTIN SHINO

NEPHELINE SY. 45
 POTASH SPAR 10.8
 SPODUMENE 15.2
 BALL CLAY 15.
 KAOLIN 10.
 SODA ASH 4.

BOB'S GREEN

CORNWALL STONE 2540
 WHITING 608
 GERSLEY BORATE 172
 COPPER CARBONATE 680
 BENTONITE 2.5%

ST JOHN'S BLACK

ALBANY SLIP 90
 NEPHELINE SY. 5
 COBALT OXIDE 5

WASHES

#6 TILE CLAY
 2% BENTONITE
 SLIGHTLY HEAVIER
 THAN WHOLE MILK



AUKLES-RANKIN WHITE SLIP

SILICA 1
 POT. SPAR 1
 BALL CLAY 1
 AVERY KAOLIN 1

3% BENTONITE

SUGGESTED SALT CLAY BODY

70 MISSOURI FIRE CLAY
 10 BALL CLAY
 20 #6 TILE CLAY (KAOLIN)
 9 FELDSPAR
 10 FINE GROL

AVERY KAOLIN 85
 NEPHELINE SYENITE 15

BLACK PIGMENT	
MASON STAIN No. 6600	50
GERSLEY BORATE	50

SANDY SIMON - 1994 - Summer

FLASHING SLIPS FOR WOOD SALT

+ BAUER DRABE

DM4 - 4190
EPK - 4190
ZIPLO 1050
BORAY - 570
Bent. 290

+ HELMER SLIP

HELMER KAOLIN - 1000
BENTONITE - 200

+ SHINO SLIP

SODA ASH 3.20
SPODUMENE - 12.14
KONA F-4 . 8.64
NEPHELINE SYENITE . 36.00
EPK. 28.00
DM4 BALL CLAY - 12.00

GLAZES. SALT - WOOD GAS.

+ POB'S GREEN

CORNWALL STONE - 75
WHITING - 18
GIBBSTON BORATE - 5
COPPER CARB. 10
BARIUM CARB. 10
BENTONITE - ?