

*peter Beasecker
1987*

TECHNICAL STATEMENT

Porcelain Body

*c/9-10 ← slump at 10 easy
if thin thrown*

Grolleg	15
6-Tile	10
EPK	10
Avery	10
XX Sagger B.C.	10
Kona F-4 Spar	15
Custer Spar	5
Flint	15
Pyrax	<u>10</u>

100

Macaloid .5%

Because of its multiple ingredients, this body is very diverse. It works well as slip, fitting at a wide range of dryness.

I use the following black stain formula for anything I want to go black. 2-5% in glazes, 8-10% in slips.

Iron Chromate	51
Cobalt Carb.	21
Black Nickel Ox.	9
Black Iron Ox.	15
Chrome	<u>4</u>

100

GLAZES c/9-10

Used in salt kiln in a medium reduced atmosphere. Usual salting is 2-4 pounds in a kiln one year old.

AVERY SLIP c/9-10

Avery	60
Neph. Sy.	<u>40</u>

100

Zinc	2%
G. Borate	2%

Note: Used on bisque ware as a glaze.

K&M Company
Torrance, CA 90503
FOLY-W
#PV19E