

Molly Cawgill
MFA Thesis Alfred NY
May 1974

Clay Bodies

C / 10-11 porcelain body for throwing

Grolleg	45
Ball clay	10
Custer feldspar	25
Flint	20

500
x 8
4000

300
x 8
2400

200
x 8
1600

C / 10-11 porcelain body for casting

Grolleg	500
Custer feldspar	300
Flint	200
Darvan #7	8%
H ₂ O	40%

500 → 4000

300 → 2400

200 → 1600

8% → 64

40% → 3200

400
x 8
3200

18
1987
1952
35

4000
2400
1600
64
3200
11264

Vivikas Clear - w/ celadon:

Whiting	19.6
Flint	32.9
EPK	28.0
Kona A ₂ Spar	27.5

Clear: 2% zinc
celadon 2.5% R10
Bluish 3% Barnard.

Randalls Barium celadon Δ10-11

Cornwall stone	43
Barium	16
Whiting	10
Talc	10
kaolin	5
calcined kaolin	16
Bentonite	2%