

CLAY BODIES

Bruce Cochrane (Alfred)  
Earthenware Body c06-04  
Ball Clay 10  
Cedar Heights  
    Redart Clay 70  
Plainsman Redstone 20  
Add: 3124 3  
    Red Iron Oxide .25

Kathy Ervin (Kansas City)  
Earthenware Body c04  
Talc 10  
Ball Clay 10  
Calvert Clay 10  
Cedar Heights  
    Redart Clay 60  
Fireclay 10

Earthenware Body (Kansas City)  
Redart 60  
Goldart 15  
Pine Lake 15  
Talc 10  
Barium pinch

Rob Forbes (Alfred)  
Brown Earthenware c04  
Ocmulgee Clay 25  
Redart Clay 25  
PBX Fireclay 20  
Calvert 10  
Talc 5  
Neph Sy 5  
Flint 10  
Barium Carb .5

Rob Forbes (Alfred)  
Sculpture/Handbuilding  
Earthenware c04  
Grog (coarse/fine) 30  
PBX Valentine 20  
Ocmulgee Clay 20  
Redart Clay 15  
Talc 8  
Neph Sy 7  
Bentonite 2  
Barium Carb .5

Terra Cotta Clay c06-02  
Redart 100  
Goldart 40  
Ochmulgee 40  
Talc 17  
Barium 3/4 cup  
Sand 12

John Gill  
Terra Cotta c04-02  
Redart 50  
Goldart 20  
Calvert (OM4) 10  
Pine Lake AP GREEN 10  
Talc 10  
Barium Carb .5  
\*Add 5-15% fine grog for  
handbuilding

Terra Cotta (Alfred) c04-02  
Ocmulgee 25  
Redart 25  
PBX (HAWTHORN BOND) 20  
Calvert 10  
Neph Sy 5  
Talc 5  
Flint 10  
\*add 5-15% fine grog for  
handbuilding

Betty Woodman's  
White Earthenware c04-02  
Kaolin 100  
Ball Clay 100  
Pine Lake 100  
Wollastonite 25  
Fine Grog 25  
Talc 10

Donna Polseno's  
White Earthenware c04-02  
AP Green. 100  
OM4 30  
Talc 30

HAWTHORN  
BOND

1/2 AP GREEN  
1/2 GOLD ART