

# RON MEYERS / Anderson Ranch - 1992

CLAY BODY: Red EARTHENWARE CONE 06-5

80 LBS. OCMULGEE  
25 RED ART  
10 BALL CLAY  
10 FIRE CLAY  
3 TALC  
5 GROG (To Taste)

AVAILABLE FROM:  
HIGHWATER CLAYS  
P.O. BOX 18284  
292 RIVERSIDE DR.  
ASHEVILLE, NC 28814  
704-252-6033

## SLIP / WHITE

FLINT 550 gms.  
BALL CLAY 150  
FRIT 3110 150  
F-4 SPAR 100  
OPAX 50  
BENT. 65

PINCH OF EPSON SALTS

Can be applied to clay at any stage except bisque

## BLACK SLIP

RED ART 800 gms  
BLACK COPPER 50  
RED IRON OX 50  
MANGANESE DIOX 30  
COBALT OXIDE 25

~~over~~

## GLAZE Δ 02-5

### CLEAR

FRIT 3124 80  
KAOLIN 10  
FLINT 10 + Epson  
Salt

FOR WHITE ADD:

OPAX 10

+ Epson Salts

## HANDLE MATERIAL:

Round Reed #2 & #4 SMOKE

AT: H.H. PERKINS

10 S. BRADLEY RD

WOODBIDGE CONN. 06525

203-389-9501

& North Carolina Basket Works  
1808 PHILLIPS DRIVE,