

Summer '93 - Randy Johnston & Jan McEachie

Glazes 404

<u>Batz Clear (Amber)</u>	3124	86.21
	EPK	10.35
	Barium Carb.	<u>3.45</u>
	Bentonite	4%
	Burnt Umber	6%

<u>Copper Blue</u>	Colemanite	38.70
	Lithium	4.20
	Neph Sy	10.00
	EPK	5.40
	Flint	<u>41.70</u>
	Copper Carb.	4%

<u>Symon Clear</u>	Lithium	3.8
	3124	75.5
	Neph Sy	9.4
	Bentonite	1.9
	EPK	<u>9.4</u>

<u>La Jolica</u>	
3124	6600
F-4 spar	1700
EPK	1100
Neph Sy	600
Zircopax	1500
Bentonite	200
Iron Ox	<u>25</u>

Stains to decorate over this glaze are mixed equal parts with Gerstley Borate.

To mix 2 cup amounts:

- 3 Tsp. stain
- 3 Tsp. Gerstley borate

these are approximate - you must mix to taste