

K.C. Waxy Navy Blue Δ04

Pemco Lead fr.H 197	74
Eclairt	13
Flint	4
E.P.L.	9
Cobalt Carb	1.5%

thick, dark, blue.

MARSH DRY BASE Δ04

kaolin	40
Frit 3110	10
Soda Ash	10
F-4 spar	10
Neph sy.	10
Magnesium Carb.	10
Lith Carb	5
Frit 3247	5

Linda Thorn
Senior Glazbook
Alfred NY 1988

Bills Basic white Δ04

Alfred '87
Cammie

Frit 3124	65.77
Kona F-4	17.44
Tile 6	10.82
Neph sy	6.29
Zircopax	14.0
Rutile	.5

Green (break red where thin) Δ06

Alfred 1987

Flint	70
Lithium	38
Frit 83	36
E.P.L.	20
Boneash	20
F-4 Soda	12
Bentinite	2
RI O	10
Copper Carb	4

Hilary Fuchs
Alfred NY 1987.

Bob Shays Moon Dog Δ06

Magnesium Carb	50
kaolin	20
Lithium Carb	10
Barax	40
Gerstley Borate	20
Cu Carb	10

Cammie Norman
Senior glaze book
Alfred NY 1988

When breaks up into islands of texture, thicker application the more the islands will separate.

Varda Blue Δ04

Neph sy.	19
Barium	40
Lithium	5
Flint	10
E.P.L.	19
Cu CO ₃	7

pete Smith/Varda
Senior glaz book
Alfred 1988

deep deep blue green dry

Lizard Δ06

Magnesium Carb	40	Cammie Norman
Lithium Carb	15	Senior glaze book
Barax	10	Alfred NY 1988
Ger. Bor.	7	
Flint	5	
Neph sy.	70	
Chrom.	.4	

light green w/ lizard type texture.

Ocean Gl (Bob Shays) Δ06

kaolin	10	Cammie Norman
Lithium Carb	30	Senior glaz. bk.
Barax	20	Alfred NY 1988
Ger. Borate	40	
Cu Carb.	4	

Matte glaze, runny, goes from blue to specks of tan. This glaze isn't all that describable.

Bob Shays Lichons Δ06

Magnesium Carb	50	
Lithium Carb	10	
Barax.	50	Cammie Norman
Gerstley Borate	30	Senior Glaze book
Copper	4	Alfred NY 1988
Cobalt Carb	.4	

has an even texture over surface,
similar to Bob Shays Moon Dog.