

PAM/TIM CLEAR cone 04-03

Gerstley Borate.....	55
Flint.....	15
E.P.K.	30
Burnt Umber.....	1-8%

IAN'S CLEAR cone 04-03

Frit 3124.....	30
E.P.K.	10
Nepheline Syenite.....	10
Lithium Carbonate.....	4
Bentonite.....	3

JOHN'S BLUE cone 05-03

Frit 3110.....	76.3
Gerstley Borate.....	5.7
E.P.K.	7.1
Flint.....	10.0
Copper Carbonate.....	6%,2%

PAUL'S MAJOLICA cone 04-03

Frit 3124.....	55
E.P.K.	30
Flint.....	15
Zircopax.....	17

BATZ MAJOLICA cone 05-04

Frit 3124.....	100
Barium Carbonate.....	4
E.P.K.	15
Zircopax.....	20

Best to size this glaze for ease in decorating with additions of corn syrup or liquid laundry start or CMC gum or spray gum on after glazing. use bacteriostat. Tint this white with tiny amount of Rutile (Up to .25%) or yellow stain.

G-76 (J. RICE) cone 07-8

Gerstley Borate.....	38
Potash Feldspar.....	37
Barium Carbonate.....	14
Flint.....	11
Bentonite.....	1

Very versatile glaze. Good with 1-8% Black Iron Oxide. Excellent with color. Can be made to fit a range of bodies. Iron additions must be ball milled for 6 hrs.

LOW FIRE SLIP cone 04

E.P.K.	25
Ball Clay.....	25
Gerstley Borate.....	25
Flint.....	25

SALT SLIP cone 9-11

Cornwall Stone.....	1 (by parts)
Kaolin.....	1
Flint.....	1
Manganese.....	5%
Copper Carbonate.....	3-5%

ASH GLAZE cone 9-11

Ash.....	33
Custer Feldspar.....	33
Ball Clay.....	33
Zircopax.....	10%

ASH GLAZE cone 9-11

Ash.....	33
Custer Feldspar.....	33
Kaolin (E.P.K.).....	33

GREEN ASH GLAZE cone 9-11

Custer Feldspar.....	33
Albany Slip.....	33
Ash.....	33

GREY cone 9-11

Nepheline Syenite.....	80
Algae/Ash.....	20

ASH GLAZE cone 9-11

Algae.....	33
Custer Feldspar.....	33
Ball Clay.....	33

RAKU CLEAR cone 03

Gerstley Borate.....	80
Clay.....	20

ASH GLAZE cone 9-11

Ash.....	33
Custer Feldspar.....	33
Algae.....	33