

All glazes should be tested before use on dinnerware

Gills WOM C04

77 Frit 3124
7 Whiting
14 Kona F-4
2 EPK
100
+10% Zircopax
5% Tin Ox.
1% Bentonite

Lead Satin Matt C06

6 Neph. Sy.
7 Flint
10 Talc
33 Gerstley Borate
6 Dolomite
4 EPK
34 Frit 3498 (Toxic Material) *3602 LEAD 3602*
100
Glaze should not be used with dinnerware

Lead Matt

9 Custer Feldsapr
9 Flint
10 Talc
33 Gerstley Borate
6 Dolomite
4 EPK
34 Frit 3498 (Toxic Material) *3602 LEAD 3602*
100
Glaze should not be used with dinnerware

Semi Opaque Soft Satin

65 Frit 3124
10 Dolomite
5 Zinc Ox.
15 EPK
5 Flint
100

Soft Semi Opaque

48 Frit 3124
20 Frit 3110
12 Zinc Ox.

10 EPK
10 Whiting
100

Clear C05

50 Frit 3124
30 EPK
20 Flint
100

White Transparent

46 Kona F-4
13 Whiting
13 Barium Carb. (Toxic Material)
12 Gerstley Borate
10 Flint
3 Zinc Ox.
100

Birdstal/Worthington Clear

55 Gerstley Borate
15 Flint
30 EPK
100

Viscous White C06-04

57 Frit 3124
15 EPK
28 Flint
100

Froth Glaze C06-04

100 Frit 3124
30 Barium Sulphate (Toxic Material)
2 Tin Ox.
1 Bentonite

133

Glaze should not be used with dinnerware

Loughrans Clear C03

90 Frit 3195
10 Ball Clay
1 Magnesium Carb.
101