

BOB SHAY'S GLAZE RECIPE CHART

CONE 06-04 1015°C → UP OXIDATION MATT-TEXTURES WIDE TEMPERATURE RANGE	MAGNESIUM CARBONATE	KAOLIN	LITHIUM CARBONATE	BORAX	GERSTLEY BORATE	COPPER CARBONATE	SILICA (FLINT)	BENTONITE	RUTILE	IRON OXIDE	COBALT CARBONATE	COBALT OXIDE	BALL CLAY	TALC	MANGANESE DIOXIDE	ZIRCO PAX	NEPHELINE SYENITE	CHROME OXIDE	WHITING
LICHENS	50		10	50	30	4					0.4								
LIZARD	40		15	10	70		5										20	0.4	
FLAMEDROPS	40		20		70	6												0.3	
MOON	50	20	10	40	20	10													
CRATERS	20	20	60	30		12	60	10											
BEADS	50			40	50		10									10			
CARBON	30			80	60				30	40		7							
EARTH MOTHER			30		30	3	20				1		10	10	3				
OCEAN OIL		10	30	20	40	6													40
SUPERSTITION			30		40	3						0.5		30			10		

SURFACES · SKINS · TEXTURES · THINGS ON CLAY.

Sackus Base
 G.P. 30
 N.S. 5
 EPK 5
 Flint 12
 Lithium 2
 HM 2
 SP 1