

Navier's Dry

Δ1-2

<u>White</u>	Neph. Sy.	—	200
	SOBWITE	—	65
	WHITTING	—	25
	SER. BORATE	—	60

Δ1-2

Neph. Sy. white	—	100
CHINA CLAY	—	60
Whittins	—	40

Δ-6-7

CHINA CLAY	—	30
WHITTING	—	40
FELDSPAR POTASH	—	30

ADD SLIDES FOR  
COLOR

MATT BASE Δ5-6

CUSTER	—	40
FRITT 3124	—	9
TALL	—	9
WHITTING	—	16
EPK	—	10
FLINT	—	16

D. RHODES - CLAY & GLAZES FOR THE POTTER (NK 4225-R 4F)

Chapter 20 SLAKE TEXTURES

CHAPTER 21 SOURCES OF COLOR IN GLAZES