

Pink Base**C 6****Oxidation****BASE RECIPE****BATCH: Gm**

Gerstley Borate	20.68	103.4
Nepheline Syenite	16.29	81.4
EPK	11.34	56.7
Whiting	19.52	97.6
Flint	32.16	160.8
		499.9

Color: Opaque pink**Surface: Shiny or Glossy****COMMENTS:**

Good as a clear or with other colorants or stains, although it may craze and be opalescent if thick. You must use a Chrome-Tin Pink Stain to get a good pink, Manganese-Alumina stains don't work well with this glaze. This glaze makes a reasonable clear without colorants, but tends toward having the opalescent white patches typical of boron glazes, especially if applied thicker. Richard Burkett 1990.

HEALTH HAZARDS:

Flint: free silica-wear a NIOSH approved dust mask when handling dry material

Chrome Oxide: all chromium compounds should be viewed as potentially carcinogenic

**ADD THESE
COLORANTS:**

Tin Oxide	5.00%	25.0
Chrome Oxide	0.15%	0.7
	%	
	%	

Estimated cost per 499.9 Gm batch: 0.75

Estimated Thermal Expansion: 74.52 x10⁻⁷

Glaze type: Ca B