

off white satin matt

AG

Barium 5.2
 Custer Spar 53.5
 Whiting 19.5
 EPK 16.0
 Flint 5.8
 Zinc Ox 9
 Rutile 6

Good SAFE LINER GLAZES

LANSE'S BINN'S CELEDON (Amber) * // Abany

CUSTER SPAR 27.5
 FLINT 20.7
 WHITING 20.7
 BALL CLAY 10.5
 GERST. BORATE 9.2
 ZINC OX 6.9
 R.I.O. 3.6

Rebecca's clear

good
does
not
craze

Neph Sy 300
 Ger. Borate 210
 EPK 100
 wollastonite 80
 Flint 310

* BLACK BIRD SATIN

CUSTER 34.2
 Whiting 12.1
 Zinc Ox 25.3
 EPK 4.0
 FLINT 22.4
 BENT. 2
 great w/ color.

* Bone white satin matt

Custer 37.6
 EPK 14.0
 Whiting 11.2
 Dolomite 8
 Gerst Borate 8
 Opax/Sparax 20

off white satin matt

AG

Barium 5.2
 Custer Spar 53.5
 Whiting 19.5
 EPK 16.0
 Flint 5.8
 Zinc Ox 9
 Rutile 6

Good SAFE LINER GLAZES

LANSE'S BINN'S CELEDON (Amber) * // Abany

CUSTER SPAR 27.5
 FLINT 20.7
 WHITING 20.7
 BALL CLAY 10.5
 GERST. BORATE 9.2
 ZINC OX 6.9
 R.I.O. 3.6



Rebecca's clear

good
does
not
craze

Neph Sy 300
 Ger. Borate 210
 EPK 100
 wollastonite 80
 Flint 310



* BLACK BIRD SATIN

CUSTER 34.2
 Whiting 12.1
 Zinc Ox 25.3
 EPK 4.0
 FLINT 22.4
 BENT. 2
 great w/ color



* Bone white satin matt

Custer 37.6
 EPK 14.0
 Whiting 11.2
 Dolomite 8
 Gerst Borate 8
 Opax/Sparax 20



	lt Blue Matte	LatIn Blot	Gold Mat	Chun Green Flkt	DK Blue	Bates Res Mat	Pratt White	Tubyls Opal	Bright Dark Celadon	Bates Glass
Barium	20		7			22				
Dolomite	12		5				20			
GB	13		15	15	27			12.5	18	
NephSy	35			20	39	60	50			
ZircO	10									
EPK	5	7		15	8			10.3		
Flint	5		31	15	18	8		30	40.5	
Albany		77								
Mag Dio		16								
Custer			33					55.6	54	
Talc			7							
Zinc			9	5				10	13.5	
3110				25						
Whiting				5	8		5	18.6	40.5	
lith Carb						5				
Ball						8	20		20.5	
F4										
Tin							5			
Illman.				1						
Black Nicle			1 1/2							
RIO			1		2				7	
Copper	1/4			3/4						
Cobalt	3/4				1/2					
RU TIL	4		4	3						

Smooth Clear Δ6

Custer 27
GB 32
EPK 14
Flint 27

Fat Cream Δ56

NS. 45
GB 25
Flint 20
Ball 10
Zirco 8
Rutile 1

Clean Δ5

Custer 35
GB 20
BaCO₃ 5
CaCO₃ 4
Zinc 2
Kaolin 7
Flint 27

Low Clean Δ5

Custer 26
3134 14
Dolo 6
BaCO₃ 5
CaCO₃ 10
EPK 14
Flint 25

MID RANGE

.35 GLAZE

ALBANY SLIP	250.3
CORNWALL ST.	96
BALL CLAY	40
FLINT	93
WHITING	34
ZINC OX.	17
RED LEAD	214

.15 GLAZE

FELDSPAR	868
FLINT	487
COLEMANITE	406
WHITING	29
ZINC OX.	63
BAR. CARB.	126
TIN OXIDE	7%

.16 1/8 O/R

NEPH. SY.	30
SPODUMENE	20
COLEMANITE	6
FLINT	13
MAG. CARB.	9
WHITING	17
GEORGIA KAOLIN	5

MATT A 4/8 O/R

WHITING	12
NEPH SY.	60
ZINC OX.	29
GEORGIA KAOLIN	16
FLINT	2

DRY MATT Δ 6 O/R

NEPH SY.	35
FELDSPAR	35
KAOLIN	5
FLINT	10
WHITING	15
1 RON 3-4% - 0.10% UO ₂	
RUTILE 4% yellow tan.	

SEMI MATT Δ 6

WHITING	9.8
TALC	2.1
BAR. CARB.	11.0
CALCINE TIN OX	4.3
SOFA FELDSPAR	42.5
KAOLIN	8.3
BALL CLAY	8.0
FLINT	14.0

SOFT PASTEL MATT Δ 6 C

FELDSPAR	30
WHITE LEAD	30
ZINC OXIDE	3
FLINT	17
RUTILE	5
WHITING	5
KAOLIN	5
TIN OXIDE	5

Δ5 MIDGLAZES

FU6 BLACK
 BASE PLUS
 COPPER CARB. 3.5%
 MANG. DIOX. 4.5%
FU6 GREEN
 BASE PLUS
 IRON OXIDE 4.5%

EPK -15
 NEDA 54. -35
 LEAD BIKINC. -10
 WHITE LEAD -10
 CaCO₃ -15
 ZnO₃ -5

light
cream
green

PV WHITE
 PV CLAY 50
 COLEMANITE 50
 ZIRCOPAX 50

SiO₂ 24
 EPK 10
 P SPAR 40
 CaCO₃ 10
 DOLOMITE 15

Dry
white

NURSES SHOE WHITE

SiO₂ 270
 EPK 100
 SPAR 950
 COLEMANITE 400
 BaCO₃ 100
 TALC 150
 ZIRCOPAX 190

COPPER RED

3134 30
 3124 30
 BALL 15
 ZNOX 10
 SiO₂ 15
 CuCO₃ 3/0 - mottled

runny
transparent

Δ5 STAINS

- 1.) IRON -1
MANG DIOX -1
- 2.) POT DIC. -1
GR. NICKEL -1
- 3.) POT DIC. -1
COBALT -1
- 4.) YELLOW OCHRE -1
COBALT -1/2
- 5.) GR. NICKEL -1/2
- 6.) YELLOW OCHRE -1
CHROME 1/2

- 7.) CHROME -1
COBALT -1/2
- 8.) RUTILE -1
- 9.) RUTILE -1
IRON -1
- 10.) RUTILE -1
IRON -1/2
ALUMINA -1
ZIRCOPAX -2
- 11.) COBALT -2
MANG. DIOX. -1/2

- 12.) ALUMINA -1
GR. NICKEL -1
POT. DIC. -1
COB. CARB. -1
- 13.) COBALT -1/2
CALCIUM -1
ZIRCOPAX -1

66

Insulator Blue

Kona F-4	48
flint	21
Grollege	9
GERSTLEY Bor.	8
Whiting	7
Talc	2
Zinc	5
Cobalt Carb.	5%.
Bentonite	3%.

SHINO

Neph Sy.	31
Spodumine	22
GERSTLEY Bor.	5
Soda Ash	4
OM4 Ball	15

CRAWL GLAZE

Neph Sy	70
Magnesium Carb	30
Bentonite	2
Kutite	5%.

White Stoneware

EPK	15
Tile #6	20
Gold ART	15
XX Sagger	10
Kona F-4	6
TRIT 3124	10
flint	13
Bent	2
Kyrax	8

SLIP

Avery Kaolin	15
EPK	20
OM4 Bull clay	30
Kona F-4	10
flint	10
TRIT 3124	5
Zircopax	5

for Green add:
Copper Carb. 4%.