

TONY HEPBURN - 1992

SALT slips. Wet to Leather Hand application

ORANGE flash

Avery Kaolin	50
E.P.K. KAOLIN	20
Neph Sy.	20
Flint	10

White base

Evolveg Kaolin	30
Xx Saggen	30
Tile #6 Kaolin	10
Kona Feldspar	15
Flint	15
+ Bentonite.	2%

For Black to White base add.

Red Iron	5
Mang Ox.	3
Cobalt Carb	2

For Blue.
add

5% Cobalt ox.

For Green
add

6% Rutile
3% Cobalt.