

LAWTON WKSHPOther Materials:

Crocus Martis	1/2 #
Yellow Iron Oxide	1/2 #
Selection of Ceramic to add to SIGG. + Glazes	1/4 # ea.

Glazes: bases w/o colorantsSandy Scot Raku

Gerstley Borate	+ 33
Spodumene	+ 17
Lepidolite	+ 17
Lithium Carb	+ 17
Superox	+ 17

BBI

Lith Carb	+ 8.7
Kaolin	+ 20.5
Frit 3819 (P25)	+ 60.0
Silica	+ 7.0
Wollastonite	+ 13.8

Jacquies Adjusted

Lith Carb	+ 5
Silica	+ 35
Gerstley Borate	+ 40
Nepheline Syenite	+ 15
Kaolin	+ 5

Clear Crackle

Gerstley Bor	+ 70
Neph Sye	+ 20
Kaolin	+ 10

LAWTON WORKSHOP

Clay Body: Red Rock Red
(Please have fine Grog or kyanite
to wedge in)

Firing Materials:

* Copper Sulfate	10-15 #s
* Iron Sulfate	10-25 #s
* Potassium Dichromate	2 #s
Vermiculite	4-8 cu. ft.
Hay or Straw	1 bale
Coal or Coke	25 #s
Scrap Copper or Brass	
Aluminum Foil	200 ft

Household Garbage:

Fruit peels esp bananas
Grains + cereals
Coffee grounds
bones + egg shells
cheap dog food

Whatever
you can
collect
store in
freezer

* available from Standard Ceramics
(A12) 276 6333

