

HIRONDELLE RAKU

CLAY BODY Δ06

LINCOLN FIRE CLAY	40
BALL (OM4)	10
TALC	20
GROG (ION)	30

GLAZE DRY LITHIUM RAKU

SILICA	55
LITHIUM	30
KAOLIN	14
BENTONITE	3

ADDITIONS:

GREY-BLUE >	RED IRON OXIDE	1
	COBALT CARB.	1/4
PURPLE >	MANG. DIOXIDE	4
	COBALT	1
RUST >	OCHRE	4
	R. I. O.	2
GIOLI (TEACH) >	RUTILE	4
	COPPER CARB.	1/2
CELEDON >	MANG. DIOXIDE	5
	COPPER CARB.	3
COPPER RED >	COPPER CARB	3
	R. I. O.	1