

VC 49R Glazes

VC Spod, 49-R

Custer Spar - 30
 Spodumene - 20
 Dolomite - 22
 EPK - 25
 Whiting - 4
 Tin oxide - 5

+ WOLLASTONITE - 4
 Bone ash - 3

VC OSW 49R

Custer Spar - 40
 Talc - 3
 Wollastonite - 3
 EPK - 20
 Whiting - 16
 Bone ash - 4
 Iron oxide - 4
 Rutile - 1

SMOOTH/SATIN/SILKY MATT.
VC T. Matt White

F/4 Feldspar - 24
 Custer Spar - 19
 Whiting - 9
 Dolomite - 10
 Talc - 6
 EPK - 4
 Calcined Kao. - 14
 Flint - 12

- Bentonite - 2%

VCES - 49R

Custer Spar - 50
 Whiting - 20
 Bar. Carb. - 16
 EPK - 14
 100

+ yellow ochre - 5
 Rutile - 3
 Bone ash - 2

VCGC 49R

Neph. Sparite - 23
 Lith. carbonate - 16
 Gersley Borate - 6
 Wollastonite - 6
 Talc - 13
 Barium Carb. - 10
 EPK - 8
 Flint - 18
 100

+ Rutile - 4
 Yellow ochre - 4
 Bone ash - 4

all matt stone/like glazes - all
 give earthy colors, from ----
 white, to creamy white, to
 tan, to orangish brown and
 red rust, to brownish.

17K (GLOSSY CHAQUE)
(WHITE)

Custer Feldspar	- 40
Flint	- 24
EPK	- 2
Whiting	- 2
Wootley Borate	- 8
Dolomite	- 8
Zinc Oxide	- 2
Barium Carbonate	- 4
Tin Oxide	- 3
Incopax	- 10

(SUPERPAX TIN IS NOT NEEDED)

17K (GLOSSY CHAQUE)
C/QR (saturated IRON)

Custer Feldspar	- 53
Whiting	- 12
Barium Carbonate	- 2.5
Zinc Oxide	- 2.5
Flint	- 24
EPK	- 6

+ 8% IRON OXIDE
- BLACK WHERE THICK
- RUSTY BROWN WHERE THIN

ELOY. STONE MATT C/QR
(ABF).

Custer Feldspar	- 54
Whiting	- 3
Dolomite	- 18
EPK	- 25

3.5% MASONS BLACK GLAZE STAIN
FT, DARK GREY, slightly Bluish

LP. MATT C/QR. SATIN/MATT

KONA F/4 feldspar	- 30
Dolomite	- 20
Kaolin	- 25
Barium Carbonate	- 15
Flint	- 10

+ Cobalt Carbonate - 1%
Granular Manganese - 1/2%
Grey blue, turning dark to black where thin.

ANER GOLD. SATIN MATT C/QR
Gold color with flecks of red.

Custer Feldspar	- 53
Kaol	- 4
Calcined Kaolin	- 10
EPK	- 15
Whiting	- 21
BONE ASH	- 3

IRON OXIDE ——— 2.5%
RUTILE ——— 2.5%

VC MATT "R". STONE MATT
TAN. RUST. GOLD FLECKS.
Creamy TAN TO RUST.

Custer Feldspar	- 26
Dolomite	- 26
EPK	- 24
Whiting	- 8
Flint	- 8
TIN OXIDE	- 8
100	

IRON SLIP. TO USE UNDER GLAZES
NOT BY ITSELF.

will bleed up through most glazes
as rusty brown to Brown colors.

ALBANY SLIP	- 50
BARNARD	- 40
Neph. SY	- 10
100	

Use used on bisque ware - to oxidize
for other glazes.

WIRT SHINO. C/QR THICK → GLOSSY GREYISH
THIN → RUSTY ORANGE -

Kona F/4 feldspar	- 18.5
Spodumene	- 15.
Soda Ash	- 4.
Neph. Syenite	- 45.5
TENN. Ball clay	- 16.

+ Bentonite - 1%