

6) GLOSSY ELECTRIC BLUE: Base glaze (1) plus ---  
 + 5% ZINC OXIDE  
 5% FRIT 3124  
~~1~~ 1% NICKEL CARBONATE → (1%)  
 2% COBALT CARBONATE.

7) GLOSSY CHINA RED: (CAN NOT BE DONE AT THIS TEMP. IN OXIDATION FIRING.)\*  
 (MAROON)  
 Put glossy crimson "ish" red, would be ---  
 Base Glaze # (1) plus + 10% MASONS CRIMSON STAIN

8) SATIN SKY BLUE CIA EX.

- CUSTER FELDSPAR - 12
- KONA #14 SPAR - 30
- GERSTLEY BORATE - 12
- TALC - 14
- DOLOMITE - 8
- EPK - 4
- FLINT - 20
- 100%

"BASE" GLAZE FOR SATIN TEXTURE (SEMI-OPAQUE).

SKY BLUE: plus + 1% COBALT CARB.  
 1/4% MANGANESE DIOXIDE

9) SATIN COBALT BLUE: Base # (8) plus ---  
 + 2% COBALT OXIDE  
 1/2% DELPHENIUM BLUE (MASONS).

# GLAZES FOR STEVE BLUMENTHAL $\frac{1}{9}$ OX.<sup>SP</sup>

(12, 5, 7%) from (10)

OXIDATION

## 1.) GLOSSY-CLEAR (transparent) $\frac{1}{9}$ OX.

KONA FLY SPAR - 40  
FLINT - 30  
WHITING - 20  
E.P.K. KAOLIN - 10

## 2.) GLOSSY TOURQUOISE: Base glaze #1 plus ---

+ 10% GERSTLEY BORATE  
2% COPPER OXIDE (OR CARBONATE).  
 $\frac{1}{4}$ % (.25) DELPHENIUM BLUE STAIN (MASON'S).

## 3.) GLOSSY FOREST GREEN: Base glaze #1 plus ----

+ 5% GERSTLEY BORATE  
1% CHROME OXIDE  
1% COPPER OXIDE.

## 4.) GLOSSY VIOLET: Base glaze #1 plus ----

+ 5% DOLOMITE  
10% GERSTLEY BORATE  
1% CRIMSON STAIN (MASON'S)  
1% MANGANESE DIOXIDE  
 $\frac{1}{4}$ % COBALT CARB. (.25).

## 5.) GLOSSY BLACK: Base glaze #1 plus ----

+ ~~4~~ 2% MASON'S BLACK GLAZE STAIN  
2% IRON OXIDE  
2% COBALT OXIDE  
2% MANGANESE DIOXIDE

\* BEWARE - THIS GLAZE  
MAY RUN WHERE  
TOO THICK.

C/9-10 OXIDATION GLAZES • V. Lushington

10/8/84

VO1 OXB: Clear, Glossy, Bright, transparent (Base Glaze) (I)

- KONA f/4 feldspar - 50
  - GROLLEG - 4
  - FLINT - 24
  - DOLOMITE - 3
  - ZINC OXIDE - 1
  - WHITING - 16
  - BARIUM CARB. - 2
- 100

• BASE GLAZE

2:OGW: for Glossy, white, opaque (add) - ZIRCOPAX - 12%

3:OGB: for Glossy Black, (opaque) add... MASON'S BLACK STAIN - 4  
 RED IRON OXIDE - 3  
 COBALT CARBONATE - 1  
 MANGANESE DIOXIDE - 1

• Base glaze + }

4:OGT: for Glossy, Opaque, TOURQUOISE  
 GERSTLEY BORATE - 5%  
 COPPER CARBONATE - 2%  
 MASON'S DELPH. BLUE - 1/4%

• Base glaze + }

5:OGEB: for Glossy, electric BLUE  
 opaque. ZINC OXIDE - 5%  
 FRITT # 3124 - 5%  
 COBALT CARBONATE - 2%  
 NICKEL CARBONATE - 1/4%

• Base glaze + }

5:OGC: for Glossy, CRIMSON  
 SCARLET MASON'S CRIMSON STAIN - 10%

• BASE glaze + }

VO OSW: - SATIN, MATT, WHITE • C/9-10

- KONA f/4 feldspar - 32
- Custer feldspar - 10
- Gerstley Borate - 8
- Talc - 14
- Dolomite - 12
- EPK - 6
- Flint - 18

Base glaze is semi opaque white  
 for opaque white

• Base glaze + ZIRCOPAX - 8%

over →