

WHITE BASE SLIP & COLORED SLIPS FOR C/4-12 HIGH FIRE.  
 These slips should be applied when the clay is either wet or leather hard. (Do not use this slip on Dry or bisque ware).

GOOD FOR SALT TOO.

WHITE BASE SLIP. C/4-12, Wet to leather hard application.

GROLLEG KAOLIN	-	30	00
XX SAGGER	-	30	00
TILE #6 KAOLIN	-	10	00
KONA #14 FELDSPAR	-	15	00
FLINT	-	15	00

+ BENTONITE - 2 % 00

For BLACK SLIP, to white Base slip add-----  
 (OX. & RED.)

Red Iron Oxide	-	5	%
Iron Chromite	-	4	%
Mang. Dioxide	-	3	%
Cobalt Carb.	-	2	%

For BLUE, to white Base slip add-----  
 (OX. & RED.)

COBALT CARB.	-	2	%
MASONS DELPHINIUM BLUE	-	2	%

For GREEN, to white Base slip add-----  
 (OX. & RED.)

COBALT CARB.	-	2	%
RUTILE	-	4	%
CHROME OXIDE	-	1	%

For TAN/RUST, to white base slip add-----  
 (YELLOW BROWN IN OXIDATION)

RUTILE	-	4	%
RED IRON OXIDE	-	4	%
ZINC OXIDE	-	2	%

For YELLOW → (OXIDATION) to white slip add-----  
 (GREYISH IN REDUCTION)

MASONS YELLOW STAIN	-	12	%
---------------------	---	----	---

For MOTHER OF PEARL - TITANIUM DIOXIDE → 6 %